



# LUBRICANTS™

**POWER TO PERFORM™**

## HP TRANSFORMER OILS

### DESCRIPTION

HP TRANSFORMER OIL is designed for human safety and free from carcinogenic Poly chlorinated Bi-phenyls (PCB) and Poly aromatic hydrocarbon (PAH).

### PROPOSED USAGE

- Electric transformers
- Switch gears
- Circuit breakers which require insulating fluids
- Has very high oxidation stability
- Excellent ageing properties resulting in long product life

### APPROVALS

HP TRANSFORMER OIL is certified Central Power Research Institute (CPRI), Bangalore and Electrical Research and Development Association (ERDA), Vadodara

HP TRANSFORMER OIL is certified Central Power Research Institute (CPRI), Bangalore and Electrical Research and Development Association (ERDA), Vadodara

### MEETING SPECIFICATION

HP TRANSFORMER OIL exceeds IS: 335:1993 (Reaffirmed 2005) performance levels.

It also meets IS:335-2018 TYPE II UNINHIBITED.

### PHYSICO-CHEMICAL PROPERTIES

Appearance	Clear and transparent and free from suspended matter of sediments
Density at 29.5 °C, g/cc	0.8279
Kinematic viscosity, cst At 27°C At 40°C	16.46 11
Interfacial tension at 27°C	0.044 N/m
Flash point pensky-marten (closed), °C	172
Pour point, °C	-18
Neutralization value, mg KOH/g a) Total acidity b) Inorganic acidity/alkalinity	Nil Nil



# LUBRICANTS™

POWER TO PERFORM™

## HP TRANSFORMER OILS

Corrosive sulphur	Non corrosive
Electric strength (breakdown voltage) –kV(rms) a) New unfiltered oil	72
Dielectric dissipation factor at 90 °C	0.00025
Specific resistance (resistivity) a) A:90 °C b) A:27 °C	750x10 <sup>12</sup> ohm-cm 11300x10 <sup>12</sup> ohm-cm
Oxidation stability a) Neutralization value after oxidation, mg KOH/g b) Total sludge after oxidation,% by wt.	0.4 0.1
<b>AGEING CHARACTERISTICS AFTER AGEING</b>	
Open breaker method with copper characteristics	
Specific resistance (resistivity) a) A:27 °C b) A:90 °C c) dielectric dissipation factor at 90 °C d) total acidity e) total sludge	350x10 <sup>12</sup> ohm-cm 19x10 <sup>12</sup> ohm-cm 0.0025/2.08 DC NIL NIL
Presence of oxidation inhibitor,% by wt	Absent
Water content, mg/kg(ppm)	50
SK value (%)	1